



Figure 1: BSE micrographs of the L03 microstructure after annealing at 900 °C for *a)* 168 h, *b)* 1000 h, *c)* 2000 h, *d)* 4000 h, and *e)* 8000 h. The brightest phase in each image is D0₁₉, black is B2, dark gray is γ and light gray is γ'. The scale bar in *a)* is representative of all images (i.e. the magnifications are the same).